



Test Report

Number: GZHT90589291

Applicant: DONGGUAN JIAN PLASTIC & METAL PRODUCTS LTD.
NO.3-1, SOUTH GAOBU BLVD
GAOBU, DONGGUAN, CHINA
ZIP CODE: 523278
Attn: EMMY

Date: Mar 16, 2016

Sample Description:

One (1) piece of submitted sample said to be Silver stainless steel material

Standard : --
Ref. No. : --
P.O. No. : --
Buyer's Name : World Wide
Vendor : World Wide
Supplier : CHINA
Manufacturer : CHINA
Ref. : STAINLESS STEEL (430BA)
AGE RANGE: 3+
Country Of Origin : MADE IN CHINA
Goods Exported To : World Wide
Date Received/Date Test Started : Mar 01, 2016
Date Final Information Confirmed: Mar 15, 2016


Conclusion:

<u>Index</u>	<u>Test Item</u>	<u>Result</u>
1.	Soluble Lead Content Test on Metal Toy Accessories	Pass
2.	Heavy Elements Analysis	Pass
3.	Toxic Element Migration Test (19)	Pass

Should you have any query on this report, you may contact at gzfootwear@intertek.com

Authorized By:
For Intertek Testing Services Shenzhen Ltd.
Guangzhou GDD Branch

Huang Ning, Andy
Assistant General Manager





Test Report

Tests Conducted (As Requested By The Applicant)

Number: GZHT90589291

1 Soluble Lead Content Test on Metal Toy Accessories

Test Method: With Reference To Japan Toy Safety Standard 2012 Part 3 Chemical Properties Clause 2.7, 2.12, Acid Extraction Method Was Used And Soluble Lead Content Was Determined By Inductively Coupled Argon Plasma Spectrometry.

<u>Result (mg/kg)</u>	<u>Requirement (mg/kg)</u>
< 5	90

Remark: mg/kg = milligram per kilogram

The Sample Weight Of Individual Coating Of The Component Was Less Than 10 mg. Base Material With Coating Was Tested

Tested Components: Silver Color Metal With Transparent Coating.

2 Heavy Elements Analysis

With reference to Section 4.3.5.2 of the ASTM Standard Consumer Safety Specification on Toy Safety F963-11, acid extraction method was used and heavy elements migration content were determined by Inductively Coupled Argon Plasma Spectrometry.

	<u>Result in ppm</u>	<u>Limit</u>
		<u>ppm</u>
Sol. Barium (Ba)	< 5	1000
Sol. Lead (Pb)	< 5	90
Sol. Cadmium (Cd)	< 5	75
Sol. Antimony (Sb)	< 5	60
Sol. Selenium (Se)	< 5	500
Sol. Chromium (Cr)	53	60
Sol. Mercury (Hg)	< 5	60
Sol. Arsenic (As)	< 2.5	25

Remark:

Sol. = Soluble
ppm = parts per million

Since The Sample Weight Of Individual Coating Of The Component Was Less Than 10 mg. Base Material With Coating Was Tested

Tested Components: Silver Color Metal With Transparent Coating.

3 Toxic Element Migration Test (19)

With Reference To EN71-3:2013 And Followed By Inductively Coupled Plasma Optical Emission Spectrometry (ICP/OES) and/or Inductively Coupled Plasma Mass Spectrometry (ICP/MS).
When Confirmation Tests Of Chromium (III)/Chromium (VI) performed, determined by Ion Chromatography-Spectrometry (IC).

Category (III): Scraped-off toy material

Element	Result (mg/kg)	Applicant's Limit (mg/kg)
Aluminium (Al)	< 300	70000
Antimony (Sb)	< 10	560
Arsenic (As)	< 10	47
Barium (Ba)	< 10	18750
Boron (B)	< 50	15000
Cadmium (Cd)	< 5	17
Chromium (III) (Cr III) **	54	460
Chromium (VI) (Cr VI) **	< 0.1 #	0.2
Cobalt (Co)	< 10	130
Copper (Cu)	< 10	7700
Lead (Pb)	< 10	160
Manganese (Mn)	< 10	15000
Mercury (Hg)	< 10	94
Nickel (Ni)	< 10	930
Selenium (Se)	< 10	460
Strontium (Sr)	< 100	56000
Tin (Sn)	< 10	180000
Organic tin **	< 3.0	12
Zinc (Zn)	< 100	46000

Remark :	mg/kg = milligram per kilogram
	# = Confirmation of Chromium (VI) test was performed on the tested component. And the reported value of migration of Chromium (III) = migration value of total Chromium – migration value of Chromium(VI).
	** = Unless the test results were marked with "#" or "Δ", Chromium (III) & Chromium (VI) and Organic tin contents were not directly determined and were derived from migration results of total chromium and tin respectively.
	- Organic tin test result was expressed as tributyl tin.
	- As per General Court of the European Union Judgment in Case T-198/12 dated 14 May 2014, the General Court confirmed that Germany could maintain its limit value for Lead(Pb)(90mg/kg) in toys but not for Antimony (Sb), Arsenic (As), Mercury (Hg) and Barium (Ba).

Tested Components: Silver Color Metal With Transparent Coating.

This report is made solely on the basis of your instructions and/or information and materials supplied by you. It is not intended to be a recommendation for any particular course of action. Intertek does not accept a duty of care or any other responsibility to any person other than the Client in respect of this report and only accepts liability to the Client insofar as is expressly contained in the terms and conditions governing Intertek's provision of services to you. Intertek makes no warranties or representations either express or implied with respect to this report save as provided for in those terms and conditions. We have aimed to conduct the Review on a diligent and careful basis and we do not accept any liability to you for any loss arising out of or in connection with this report, in contract, tort, by statute or otherwise, except in the event of our gross negligence or wilful misconduct.

GZHT90589291

