



**Test Report**

Number: GZHT90589287

Applicant: DONGGUAN JIAN PLASTIC & METAL PRODUCTS LTD.  
NO.3-1, SOUTH GAOBU BLVD  
GAOBU, DONGGUAN, CHINA  
ZIP CODE: 523278  
Attn: EMMY

Date: Mar 16, 2016

**Sample Description:**

One (1) piece of submitted sample said to be Silver stainless steel material

Standard : --  
Ref. No. : --  
P.O. No. : --  
Buyer's Name : World Wide  
Vendor : World Wide  
Supplier : CHINA  
Manufacturer : CHINA  
Ref. : STAINLESS STEEL (430BA)  
AGE RANGE: 3+  
Country Of Origin : MADE IN CHINA  
Goods Exported To : World Wide  
Date Received/Date Test Started : Mar 01, 2016  
Date Final Information Confirmed: Mar 15, 2016


**Conclusion:**

<u>Index</u>	<u>Test Item</u>	<u>Result</u>
1.	Total Lead (Pb) Content	Pass
2.	Total Lead (Pb) Content In Non-Surface Coating Materials	Pass
3.	Total Cadmium (Cd) Content	Pass

Should you have any query on this report, you may contact at [gzfootwear@intertek.com](mailto:gzfootwear@intertek.com)

Authorized By:  
For Intertek Testing Services Shenzhen Ltd.  
Guangzhou GDD Branch

Huang Ning, Andy  
Assistant General Manager



LX/adalee



**Test Report**

Tests Conducted (As Requested By The Applicant)

Number: GZHT90589287

1 Total Lead (Pb) Content

With Reference To EPA 3050B: 1996 And EPA 3051A:2007, Acid Digestion Method Was Used And Total Lead Content Was Determined By Inductively Coupled Argon Plasma Spectrometry.

Result In ppm

Applicant's Requirement In ppm  
90

ND

Remark: ppm = Parts Per Million  
Detection Limit = 10 ppm  
ND=Not Detected

As Requested By The Applicant, The Surface Coatings Are Tested With The Substrate For Total Lead Content Test Of Tested Component (3). With The Consideration Of The Dilution Factor, The Testing Result May Not Represent The Result Of The Individual Coatings And Substrate.

Tested Components: Silver Color Metal With Transparent Coating.

2 Total Lead (Pb) Content In Non-Surface Coating Materials:

With Reference To CPSC-CH-E1001-08.3:2012/CPSC-CH-E1002-08.3:2012, Acid Digestion Method Was Used And Total Lead Content Was Determined By Inductively Coupled Argon Plasma Spectrometry.

Result In ppm

Applicant's Requirement In ppm  
90

ND

Remark: ppm = Parts Per Million  
Detection limit = 10ppm  
ND=Not Detected

As requested by the applicant, the surface coatings are tested with the substrate for total lead content test of tested component (3). With the consideration of the dilution factor, the testing result may not represent the result of the individual coatings and substrate.

Tested Components: Silver Color Metal With Transparent Coating.

---



**Test Report**

Tests Conducted (As Requested By The Applicant)

Number: GZHT90589287

3 Total Cadmium (Cd) Content

With reference to EPA 3050B: 1996 and EPA 3051A: 2007, ACID Digestion Method Was Used And Total Cadmium Content Was Determined By Inductively Coupled Argon Plasma Spectrometry.

<u>Result In ppm</u>	<u>Applicant's Limit In ppm</u>
<10	75

Remark: ppm = Parts Per Million  
Detection Limit = 10ppm

Tested Component: Silver Color Metal With Transparent Coating.

---

*This report is made solely on the basis of your instructions and/or information and materials supplied by you. It is not intended to be a recommendation for any particular course of action. Intertek does not accept a duty of care or any other responsibility to any person other than the Client in respect of this report and only accepts liability to the Client insofar as is expressly contained in the terms and conditions governing Intertek's provision of services to you. Intertek makes no warranties or representations either express or implied with respect to this report save as provided for in those terms and conditions. We have aimed to conduct the Review on a diligent and careful basis and we do not accept any liability to you for any loss arising out of or in connection with this report, in contract, tort, by statute or otherwise, except in the event of our gross negligence or wilful misconduct.*

GZHT90589287

