

**Test Report**

Number: GZHT90589370

Applicant: DONGGUAN JIAN PLASTIC & METAL PRODUCTS  
LTD.  
NO.3-1, SOUTH GAOBU BLVD  
GAOBU, DONGGUAN, CHINA  
ZIP CODE: 523278  
Attn: EMMY

Date: Mar 16, 2016

**Sample Description:**

Two (2) pieces of submitted sample said to be Yellow Twill material

Standard : --  
Ref. No. : --  
P.O. No. : --  
Buyer's Name : World Wide  
Vendor : World Wide  
Supplier : CHINA  
Manufacturer : CHINA  
Ref. : YELLOW TWILL  
COLOR: YELLOW  
AGE RANGE: 3+  
Country Of Origin : MADE IN CHINA  
Goods Exported To : World Wide  
Date Received/Date Test Started : Mar 01, 2016  
Date Final Information Confirmed: Mar 15, 2016


**Conclusion:**

<u>Index</u>	<u>Test Item</u>	<u>Result</u>
1.	Color Fastness To Washing	Pass
2.	Total Lead (Pb) Content In Surface Coating	Not Applicable
3.	Total Lead (Pb) Content In Non-Surface Coating Materials	Pass
4.	Total Cadmium (Cd) Content	Pass

Should you have any query on this report, you may contact at [gzfootwear@intertek.com](mailto:gzfootwear@intertek.com)

**Authorized By:**

For Intertek Testing Services Shenzhen Ltd.  
Guangzhou GDD Branch



Huang Ning, Andy  
Assistant General Manager



- 1 Color Fastness To Washing (ISO 105 C06 A2S-2010, Single Test, 30 Minutes Mechanical Wash At 40°C In 0.4% ECE Reference Detergent And 0.1% Sodium Perborate Solution With 10 Steel Balls):

		<u>Applicant's Requirement</u>
Color Change	4-5 Grade	Min. 4 Grade
Color Staining		Min. 4 Grade
-Acetate	4-5 Grade	
-Cotton	4-5 Grade	
-Nylon	4-5 Grade	
-Polyester	4-5 Grade	
-Acrylic	4-5 Grade	
-Wool	4-5 Grade	

Remark: This Test Was Conducted At 3F, Hengyun Building, No.235 Kaifa Avenue, GETDD

- 2 Total Lead (Pb) Content In Surface Coating

With Reference To CPSC-CH-E1003-09.1:2011, Acid Digestion Method Was Used And Total Lead Content Was Determined By Inductively Coupled Argon Plasma Spectrometry.

<u>Result In ppm</u>	<u>Requirement In ppm</u>
Not Applicable	90

Remark: ppm = Parts Per Million

Assessment: Since No Scrapable Surface Coating Was Found On The Submitted Sample(s), The Testing Scope Was Not Applicable To The Submitted Sample(s).

- 3 Total Lead (Pb) Content In Non-Surface Coating Materials:

With Reference To CPSC-CH-E1001-08.3:2012/CPSC-CH-E1002-08.3:2012, Acid Digestion Method Was Used And Total Lead Content Was Determined By Inductively Coupled Argon Plasma Spectrometry.

<u>Result In ppm</u>	<u>Requirement In ppm</u>
ND	100

Remark: ppm = Parts Per Million  
Detection limit = 10ppm  
ND=Not Detected

Tested Component: Yellow Woven.

**Test Report**

Tests Conducted (As Requested By The Applicant)

Number: GZHT90589370

## 4 Total Cadmium (Cd) Content

With reference to EPA 3050B: 1996 and EPA 3051A: 2007, ACID Digestion Method Was Used And Total Cadmium Content Was Determined By Inductively Coupled Argon Plasma Spectrometry.

Result In ppmApplicant's  
Limit In ppm

&lt; 10

75

Remark: ppm = Parts Per Million  
Detection Limit = 10ppm

Tested Component: Yellow Woven.

---

*This report is made solely on the basis of your instructions and/or information and materials supplied by you. It is not intended to be a recommendation for any particular course of action. Intertek does not accept a duty of care or any other responsibility to any person other than the Client in respect of this report and only accepts liability to the Client insofar as is expressly contained in the terms and conditions governing Intertek's provision of services to you. Intertek makes no warranties or representations either express or implied with respect to this report save as provided for in those terms and conditions. We have aimed to conduct the Review on a diligent and careful basis and we do not accept any liability to you for any loss arising out of or in connection with this report, in contract, tort, by statute or otherwise, except in the event of our gross negligence or wilful misconduct.*

GZHT90589370

